

1. SPECIAL BORROW

A. Description. Place special borrow at the locations shown in the plans, cross sections, or as directed by the Project Manager.

B. Materials. Provide material for special borrow consisting of a well-graded sand and gravel, free of organic and other deleterious material, meeting the AASHTO M 145 requirements for A-1-b group classification, with 100% passing the 6 inch sieve and a maximum of 15% by weight passing the number #200 sieve.

C. Construction. Compact special borrow in accordance with Section 203.

D. Method of Measurement. Special borrow is measured in accordance with Subsection 203.04.

E. Basis of Payment. Special Borrow is paid in accordance with Subsection 203.05.